

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property
Organization
International Bureau



(43) International Publication Date
22 April 2004 (22.04.2004)

PCT

(10) International Publication Number
WO 2004/034105 A1

(51) International Patent Classification⁷: G02B 1/11, 5/08,
C03C 17/25, 17/245, 17/34

(21) International Application Number:
PCT/EP2003/050692

(22) International Filing Date: 6 October 2003 (06.10.2003)

(25) Filing Language: English

(26) Publication Language: English

(30) Priority Data:
02/12820 10 October 2002 (10.10.2002) FR

(71) Applicant (for all designated States except US):
GLAVERBEL [BE/BE]; Chaussée de La Hulpe, 166,
B-1170 Bruxelles (BE).

(72) Inventors; and

(75) Inventors/Applicants (for US only): AUMERCIER,
Laurent [FR/FR]; 51, rue du Moulin, F-57635 Brouviller
(FR). DREIDEMY, Pierre-André [FR/FR]; 31, rue de
Verdun, F-57200 Remelfing (FR).

(74) Agents: VANDEBERG, Marie-Paule et al.; Glaverbel -
Centre R & D, Department Intellectual Property, Rue de
l'Aurore, 2, B-6040 Jumet (BE).

(81) Designated States (national): AE, AG, AL, AM, AT, AU,
AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU,
CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH,
GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC,
LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW,
MX, MZ, NI, NO, NZ, OM, PH, PL, PT, RO, RU, SC, SD,
SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US,
UZ, VC, VN, YU, ZA, ZM, ZW.

(84) Designated States (regional): Eurasian patent (AM, AZ,
BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE,
BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HU,
IE, IT, LU, MC, NL, PT, RO, SE, SI, SK, TR).

Declaration under Rule 4.17:


— of inventorship (Rule 4.17(iv)) for US only

Published:

— with international search report
— before the expiration of the time limit for amending the
claims and to be republished in the event of receipt of
amendments

For two-letter codes and other abbreviations, refer to the "Guid-
ance Notes on Codes and Abbreviations" appearing at the begin-
ning of each regular issue of the PCT Gazette.

(54) Title: HYDROPHILIC REFLECTIVE ARTICLE



(57) Abstract: The invention relates to a composite article, in par-
ticular a rear-view mirror for a motor vehicle, comprising a sub-
strate (10), generally made of glass, a reflective layer (20) com-
posed of an oxidised or nitrided metal, possibly in an under-sto-
ichiometric state, disposed on the front face (Figure 1) or on the
rear face (Figure 2). The coating stack on the front face comprises
a generally titanium dioxide-based layer (40) having photocatalytic
properties, possibly covered by a fine hydrophilic layer (50), in par-
ticular composed of silicon oxide. The coating stack possibly com-
prises a barrier sub-layer (30). The article according to the inven-
tion advantageously has an attenuated reflection which can vary be-
tween 40 and 75 %.

WO 2004/034105 A1

Hydrophilic Reflective Article

The present invention relates to a reflective article, in particular for the rear-view mirrors for motor vehicles, having hydrophilic properties and an attenuated reflection factor. The present invention also relates to a process for the production of such an article.

5 Mirrors comprising a metal layer (generally made of silver, aluminium or chromium) applied either to the rear face of a transparent substrate, i.e. on the face remote from the observer, or on the front face of the substrate, thus the face directed towards the observer, are known. With a metal layer of chromium having a thickness in the order of 40 to 60 nm, a light reflection of about 65% is obtained,
10 which is perfectly satisfactory for use as a rear-view mirror. However, with more significant light reflections the rear-view mirror has the disadvantage of causing glare for the driver.

Mirrors with a surface, which has been rendered hydrophilic, are also known (see EP 689 962, EP 1 022 588 or JP 2001033607, for example).

15 The hydrophilic character of a surface increases its surface energy, which allows drops of water to spread in a film instead of forming droplets. On a non-hydrophilic mirror the rain forms droplets, which obstruct visibility. On a mirror with a hydrophilic surface, the water spreads to form a film to allow better visibility. Various materials are known for their inherent hydrophilic properties, in particular
20 titanium oxide and silicon oxide.

In addition to its hydrophilic properties, titanium oxide, particularly when crystallised in the form of anatase, is also well known for its inherent photocatalytic properties, i.e. it is able to degrade organic matter when stimulated by light or UV irradiation.

25 Patent applications EP 978 494 and EP 1 099 671 describe anti-fog mirrors comprising a reflective metal film respectively on the rear and front face and a $\text{TiO}_2/\text{SiO}_2$ coating stack on the front face.

Since the TiO_2 layer has a high refractive index ($n=2.4$), the reflection factor of the coating stack in the visible range is elevated, in the order to 80% for a stack of neutral colouration. To reduce glare, the thicknesses of the layers must be selected so that the wavelength of the reflected light has a peak between 400 and 510 nm, which gives a reflected blue colour and a light reflection in the order of 60%. EP 1 099 671 provides that a reflection-adjusting layer can be added between the reflective film and the TiO_2 layer to prevent excessive reduction of the light reflection.

Coating stacks with alternating layers of high and low refractive index are commonly used to increase the light reflection. Documents EP 456 488 and EP 1 040 963 describe mirrors with high light reflection ($>70\%$) using a metal layer as reflective layer, and a succession of low index layers (SiO_2) and high index layers (TiO_2) to increase reflection.

There is a need to provide a reflective article with a photocatalytic and hydrophilic effect to allow good visibility in the case of rain, while maintaining a moderate reflection factor to decrease glare. It must be possible in a simple manner to provide such an article with moderate reflection in neutral reflected tones as well as in coloured tones, e.g. in the blue range.

The aim of the invention is to remedy the disadvantages described above. In particular, an aim of the present invention is to provide a reflective article, which has hydrophilic and photocatalytic properties, and a light reflection, which is maintained at a level of reflection that is not excessive even with a neutral colouration.

The subject of the present invention is a composite article comprising a substrate, a reflective layer (generally referred to as reflector) composed of an oxidised or nitrided metal, possibly in an under-stoichiometric state, possibly covered by a barrier layer, then a titanium dioxide-based layer with photocatalytic properties, then possibly a fine porous hydrophilic layer composed in particular of silicon oxide. This surface layer can be discontinuous.

In particular, the reflective layer is a Cr_xN_y wherein x is comprised between 0.67 and 0.9, preferably between 0.7-0.8 and y is comprised between 0.1-0.33, preferably between 0.2-0.3.

According to an advantageous embodiment shown in Figure 1, the layers are disposed on the same face of the substrate. However, it is also possible to dispose the reflective layer on the rear face, i.e. on the face remote from the observer, and the photocatalytic layer on the front face, as shown in Figure 2.

The thickness of the photocatalytic layer can be in the range of between 20 and 120 nm and preferably between 40 and 75 nm. This thickness of the surface layer is itself generally in the range of between 2 and 10 nm and preferably between 3 and 8 nm. This latter layer allows the hydrophilic character of the surface to be preserved for longer after the light irradiation has ceased. The very fine thickness of this outer layer enables the photocatalytic effect of the TiO_2 layer to be preserved to some extent.

When a barrier layer is disposed between the reflective layer and the photocatalytic layer, this barrier layer is advantageously composed of silicon oxide. Its thickness can lie between 10 and 80 nm and preferably between 20 and 60 nm. As a result of this barrier layer, the migration of alkaline constituents of the glass, in particular Na^+ ions, towards the titanium oxide layer can be reduced or prevented, and also the titanium oxide layer can be separated from the reflector.

The metal of the reflective layer can be selected from titanium, chromium, aluminium, silicon, zirconium and alloys of these metals. Advantageously, the reflective layer is composed of partially oxidised or nitrided chromium. Its thickness can lie between 20 and 150 nm, preferably between 40 and 120 nm.

It is advantageous if the above-described reflective article has a light reflection (integrated over the entire visible range) in the range of between 40 and 75% and preferably between 45 and 70% of the incident visible light.

When the reflected colour of the article according to the invention is neutral (i.e. when the coefficients a^* and b^* of the Lab system lie between -5 and 5), it is advantageous if the reflection factor lies between 55 and 75%, preferably

between 60 and 70%, and when the reflected colour is within the blue range (i.e. a^* lies between -10 and 0 and b^* is less than -10), it is advantageous if the reflection factor lies between 40 and 55%, preferably between 40 and 50%. The coefficients a^* and b^* are measured with the illuminant D65 at an angle of incidence of 2° .

5 The light transmission of the article must be very low and preferably less than 3%, indeed less than 2%.

The present invention also relates to a process for the production of a reflective and hydrophilic article, which comprises the following steps:

10 the deposit of a lightly oxidised or nitrided metal layer (20) on the front or rear face of a support by cathodic magnetron sputtering in a controlled reactive atmosphere with a metal target;

 possibly the deposit of an SiO_2 barrier layer on the front face of the support by cathodic magnetron sputtering in a reactive atmosphere with an Si target;

15 the deposit of a TiO_2 layer on the front face by cathodic magnetron sputtering, e.g. in a reactive atmosphere with a Ti target;

 thermal treatment at a temperature in the range of between 300 and 500°C , in particular between 350 and 450°C , for a period that may vary from 15 minutes to 6 hours, in particular from 30 minutes to 4 hours, which allows the TiO_2 to crystallise in the form of anatase while preventing crazing of the TiO_2 and the haze
20 which would result therefrom.

 In particular, a process according to the invention also comprises a step of depositing a fine surface layer of SiO_2 by magnetron sputtering in a reactive atmosphere with an Si target.

25 When the reflective layer is disposed on the rear face, this is advantageously deposited first. The barrier and photocatalytic layers and the surface layer are then deposited on the opposite face. The entire covered substrate can then be subjected to a thermal treatment.

 The present invention is described below by non-restrictive practical examples.

30 **Example 1:**

A coating stack comprising glass / Cr_xO_y / SiO_2 / TiO_2 / SiO_2 of neutral colouration, as shown in Figure 1, is formed on a clear soda-lime glass (10) with a thickness of 2 mm by cathodic magnetron sputtering.

The conditions of depositing the different layers forming the stack are as follows:

A first layer (20) of lightly oxidised chromium is deposited on the substrate (10) from a chromium metal target in an atmosphere of 80% by mass of argon and 20% by mass of oxygen. The thickness of the layer is in the order of 45 nm.

A barrier layer (30) of SiO_2 is deposited on the first layer from an Si metal target in an atmosphere of 75% by mass of argon and 25% by mass of oxygen. The thickness of the layer is in the order of 40 nm.

A layer of TiO_2 (40) is deposited on the barrier layer from an oxidised titanium target in an atmosphere of 75% by mass of argon and 25% by mass of oxygen. The thickness of the layer is in the order of 60 nm.

A last very fine layer of SiO_2 (50) is then deposited on the coating stack. The deposit is performed from an Si metal target in an atmosphere of 75% by mass of argon and 25% by mass of oxygen. The thickness of the layer is in the order of 5 nm.

The coated substrate is then subjected to a thermal treatment for 1 hour at 400°C. The rise in temperature occurs rapidly but cooling is conducted very progressively (approximately 3°C per minute).

The light reflection factor (LR) integrated over the entire visible range is measured in accordance with the standard SAE J 964 with an integrating photometer. The substrate coated according to Example 1 has a LR of 65%, while the same stack of SiO_2 / TiO_2 / SiO_2 on a chromium metal layer of the same thickness would have given a LR of 80% and would therefore have given too much glare for use as a rear-view mirror (see Figure 3).

The reflected colour of the coating stack is determined by the colorimetric coordinates L^* , a^* , b^* on the basis of illuminant D65 with an angle of incidence of 2°. The values obtained are collated in the table below. The very low

values for a^* and b^* show that the coating stack does not have any significant reflected colour.

The light transmission (LT) integrated over the visible range is 0.9%.

5 **Example 2:**

A coating stack comprising glass / Cr_xN_y / SiO_2 / TiO_2 / SiO_2 of blue colouration, as also shown in Figure 1, is formed on a clear soda-lime glass (10) with a thickness of 2 mm by cathodic magnetron sputtering.

10 The conditions of depositing the different layers forming the stack are as follows:

A first layer (20) of lightly nitrided chromium is deposited on the substrate from a chromium metal target in an atmosphere of 50% by mass of argon and 50% by mass of nitrogen. The thickness of the layer is in the order of 45 nm.

15 A barrier layer (30) of SiO_2 with a thickness in the order of 25 nm, then a TiO_2 layer (40) with a thickness in the order of 40 nm, and then a last layer of SiO_2 (50) with a thickness in the order of 5 nm are successively deposited in the same conditions as described in Example 1.

The coated substrate is then subjected to a thermal treatment under the same conditions as described in Example 1.

20 The light reflection factor (LR) integrated over the entire visible range is measured in accordance with the standard SAE J 964 with an integrating photometer. The substrate coated according to Example 2 has a LR of 43%, while the same coating stack of SiO_2 / TiO_2 / SiO_2 on a chromium metal layer of the same thickness would have given a LR of 56% (see Figure 4).

25 The reflected colour of the coating stack is determined by the colorimetric coordinates L^* , a^* , b^* on the basis of illuminant D65. The values obtained are collated in the table below. The negative values for b^* and the very slightly negative values for a^* show that the coating stack has a slightly greenish reflected blue colour.

30 The light transmission (LT) integrated over the visible range is 1.5%.

Example 3 :

A coating stack comprising glass / Cr_xN_y / SiO_2 / TiO_2 / SiO_2 of neutral colour, as also shown in Figure 1, is formed on a clear soda-lime glass (10) with a thickness of 2 mm by cathodic magnetron sputtering in the same conditions as in example 2.

The thickness of the layers are : 75 nm for the Cr_xN_y layer (20), 55 nm for the SiO_2 barrier layer (30), 50 nm for the TiO_2 layer (40) and around 5 nm for the SiO_2 top layer (50).

The coated substrate is then subjected to a thermal treatment under the same conditions as described in Example 1.

The level of nitridation of the Cr_xN_y layer has been analysed. The index x is evaluated at 0.7 and y at 0.3.

The substrate coated according to Example 3 has a LR of 68%, while the same coating stack of SiO_2 / TiO_2 / SiO_2 on a chromium metal layer of the same thickness would have given a LR of 76% (see Figure 5).

The colorimetric coordinates L^* , a^* , b^* of the reflected colour are collated in the table below. The very low values for a^* and b^* show that the coating stack does not have any significant reflected colour.

Table 1:

	LR	L^*	a^*	b^*
Example 1	65	85.8	-3.8	-1.4
Example 2	43	75.1	-6.4	-16.4
Example 3	68	76	-3.73	-2.36

CLAIMS

1. Composite article comprising a substrate (10), a reflective layer (20) and a titanium dioxide-based photocatalytic layer (40), said article being characterised in that the reflective layer (20) is composed of an oxidised or nitrided metal such that the total light reflection integrated over the entire visible range of the composite article is in the range of between 40 and 75%.

2. Article according to claim 1, characterised in that the oxidised or nitrided metal of the reflective layer (20) is in an under-stoichiometric state.

3. Article according to any one of claim 1 or 2, characterised in that the layers are disposed on the same face of the substrate.

4. Article according to any one of claim 1 or 2, characterised in that the reflective layer (20) is disposed on the rear face and the photocatalytic layer (40) on the front face.

5. Article according to any one of the preceding claims, characterised in that it comprises a barrier layer (30) between the photocatalytic layer (40) and the substrate (10).

6. Article according to the preceding claim, characterised in that the barrier layer (30) is composed of silicon oxide.

7. Article according to any one of the preceding claims, characterised in that the metal of the reflective layer (20) is selected from Cr, Ti, Al, Si, Zr and the alloys of these metals.

8. Article according to any one of the preceding claims, characterised in that it comprises a surface layer (50) on the front face.

9. Article according to the preceding claim, characterised in that the surface layer (50) is composed of silicon oxide.

10. Article according to any one of the preceding claims, characterised in that the thickness of the reflective layer (20) is in the range of between 20 and 100 nm and preferably between 30 and 60 nm.

11. Article according to any one of the preceding claims, characterised in that the thickness of the photocatalytic layer (40) is in the range of between 20 and 120 nm and preferably between 40 and 75 nm.

12. Article according to any one of the preceding claims, characterised in that the thickness of the surface layer (50) is in the range of between 2 and 10 nm and preferably between 3 and 6 nm.

13. Article according to any one of the preceding claims, characterised in that the thickness of the barrier layer (30) is in the range of between 10 and 80 nm and preferably between 20 and 60 nm.

14. Article according to any one of the preceding claims, characterised in that the light reflection integrated over the entire visible range lies between 45 and 70%.

15. Article according to any one of the preceding claims, characterised in that when the reflected colour is neutral (i.e. when the coefficients a^* and b^* of the Lab system are between -5 and 5), the reflection factor lies between 55 and 75%, preferably between 60 and 72%, and when the reflected colour is within the blue range, i.e. a^* lies between -10 and 0 and b^* is less than -10, the reflection factor lies between 40 and 55%, preferably between 40 and 50%.

16. Process for preparing a composite article, characterised in that it comprises the following steps:

- deposit of a lightly oxidised or nitrided metal layer (20) on one or other of the faces of a support (10) by cathodic magnetron sputtering in a controlled reactive atmosphere;
- deposit of a photocatalytic layer (40) on the front face of the support by cathodic magnetron sputtering;
- thermal treatment at a temperature in the range of between 300 and 500°C, in particular between 350 and 450°C, for a period that may vary from 15 min to 6 hours.

17. Process according to Claim 15, characterised in that it comprises a step of depositing a SiO_2 barrier layer (30) by cathodic sputtering prior to depositing the photocatalytic layer (40).

18. Process according to either one of Claims 15 or 16, characterised in that it comprises a step of depositing a fine hydrophilic surface layer (50) by cathodic magnetron sputtering.

19. Use of the article according to any one of Claims 1 to 14 or product according to any one of Claims 15 to 17, as rear-view mirror of a motor vehicle.

1/3




Fig 1







Fig 2

2/3

**Fig. 3****Fig. 4**

**Fig. 5**

INTERNATIONAL SEARCH REPORT

 International Application No.
 P 03/50692

A. CLASSIFICATION OF SUBJECT MATTER

IPC 7 G02B1/11 G02B5/08 C03C17/25 C03C17/245 C03C17/34

According to International Patent Classification (IPC) or to both national classification and IPC

B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

IPC 7 G02B C03C

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practical, search terms used)

EPO-Internal, PAJ, WPI Data

C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	EP 1 040 963 A (NIPPON SHEET GLASS CO LTD) 4 October 2000 (2000-10-04) cited in the application	1-15, 19
Y	paragraphs '0016!-'0022!,'0023!,'0024!-'0027!,'0066!, '0038!-'0041!; figures 1-3; table 1	15-18
A	US 5 745 291 A (JENKINSON TIMOTHY) 28 April 1998 (1998-04-28) column 3, line 9 -column 4, line 21	1-19
X	GB 2 291 653 A (GLAVERBEL) 31 January 1996 (1996-01-31) page 1, line 1-5 page 3, line 1-32 page 4, line 15-17	1-3, 7, 10
Y	page 6, line 1-9 page 9, line 7-13; example 7; table 3	15-18
	--- -/--	



Further documents are listed in the continuation of box C.



Patent family members are listed in annex.

* Special categories of cited documents :

- *A* document defining the general state of the art which is not considered to be of particular relevance
- *E* earlier document but published on or after the international filing date
- *L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)
- *O* document referring to an oral disclosure, use, exhibition or other means
- *P* document published prior to the international filing date but later than the priority date claimed

T later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

X document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

Y document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art.

& document member of the same patent family

Date of the actual completion of the International search

19 February 2004

Date of mailing of the international search report

02/03/2004

Name and mailing address of the ISA

 European Patent Office, P.B. 5818 Patentlaan 2
 NL - 2280 HV Rijswijk
 Tel. (+31-70) 340-2040, Tx. 31 651 epo nl,
 Fax: (+31-70) 340-3016

Authorized officer

Casse, M

INTERNATIONAL SEARCH REPORT

 Inte Application No
 PC 03/50692

C.(Continuation) DOCUMENTS CONSIDERED TO BE RELEVANT

Category *	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 97 10186 A (BOIRE PHILIPPE ; TALPAERT XAVIER (FR); SAINT GOBAIN VITRAGE (FR)) 20 March 1997 (1997-03-20)	1-3, 7, 11
Y	page 1, line 20-22 page 2, line 9 - page 3, line 24 page 8, line 13-21 page 10, line 23-27	15-18
X	EP 0 901 991 A (CENTRAL GLASS CO LTD) 17 March 1999 (1999-03-17) paragraphs '0001!', '0015!', '0016!', '0018!', '0026!', '0027!; claims 6, 7; figure 1	1, 3, 4, 7, 10, 11, 14
X	US 2002/045073 A1 (FINLEY JAMES J) 18 April 2002 (2002-04-18)	1
Y	paragraphs '0007!', '0012!', '0025!'-'0031!', '0034!', '0035!', '0044!', '0101!; figure 1	15-18
A	PATENT ABSTRACTS OF JAPAN vol. 2000, no. 08, 6 October 2000 (2000-10-06) & JP 2000 131513 A (TOYOTA MOTOR CORP), 12 May 2000 (2000-05-12) abstract; figures 1, 5, 6 paragraphs '0021!', '0022!; figure 2	1-18

INTERNATIONAL SEARCH REPORT

Information on patent family members

International Application No

PO 03/50692

Patent document cited in search report		Publication date	Patent family member(s)	Publication date
EP 1040963	A	04-10-2000	JP 2000347013 A	15-12-2000
			EP 1040963 A2	04-10-2000
			US 6312131 B1	06-11-2001
US 5745291	A	28-04-1998	AT 145195 T	15-11-1996
			AU 4152993 A	13-01-1994
			BR 9302815 A	22-02-1994
			CA 2099519 A1	12-01-1994
			CN 1081657 A , B	09-02-1994
			CZ 9301318 A3	16-02-1994
			DE 69305936 D1	19-12-1996
			DE 69305936 T2	17-04-1997
			DK 583871 T3	21-04-1997
			EG 20125 A	31-07-1997
			EP 0583871 A1	23-02-1994
			ES 2096864 T3	16-03-1997
			FI 933164 A	12-01-1994
			GB 2268509 A , B	12-01-1994
			GR 3022231 T3	30-04-1997
			HU 70362 A2	30-10-1995
			IL 106202 A	31-01-1996
			IN 183341 A1	27-11-1999
			JP 3434320 B2	04-08-2003
			JP 6183787 A	05-07-1994
			MX 9304101 A1	31-01-1994
			NZ 248032 A	24-02-1995
			PL 299635 A1	21-03-1994
			RU 2120919 C1	27-10-1998
			TR 26801 A	08-08-1994
			US 5505989 A	09-04-1996
			US 5580364 A	03-12-1996
			ZA 9304664 A	25-01-1994
			US 5938958 A	17-08-1999
			US 5749931 A	12-05-1998
			US 5525406 A	11-06-1996
			US 5751484 A	12-05-1998
GB 2291653	A	31-01-1996	AT 408980 B	25-04-2002
			AT 125095 A	15-09-2001
			BE 1008681 A3	02-07-1996
			CH 690302 A5	14-07-2000
			CZ 9501924 A3	12-06-1996
			DE 19526223 A1	01-02-1996
			ES 2123387 A1	01-01-1999
			FR 2722775 A1	26-01-1996
			HU 74415 A2	30-12-1996
			IL 114700 A	17-02-2000
			IT 1276499 B1	31-10-1997
			LU 88640 A1	01-12-1995
			NL 1000882 C2	15-04-1996
			NL 1000882 A1	25-01-1996
			TR 970054 A2	21-02-1997
WO 9710186	A	20-03-1997	FR 2738813 A1	21-03-1997
			AT 210097 T	15-12-2001
			AU 7087596 A	01-04-1997
			BR 9610604 A	17-02-1999
			CZ 9800784 A3	12-08-1998

INTERNATIONAL SEARCH REPORT

Information on patent family members

Int

Patent Application No

P

03/50692

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
WO 9710186	A	DE 29624343 U1	29-05-2002
		DE 29624395 U1	16-01-2003
		DE 69617705 D1	17-01-2002
		DE 69617705 T2	08-08-2002
		DK 850204 T3	02-04-2002
		EP 1132351 A1	12-09-2001
		EP 0850204 A1	01-07-1998
		ES 2168506 T3	16-06-2002
		WO 9710186 A1	20-03-1997
		JP 11512337 T	26-10-1999
		PL 325527 A1	03-08-1998
		PT 850204 T	31-05-2002
		TR 9800459 T1	22-06-1998
		US 2002071956 A1	13-06-2002
		US 6103363 A	15-08-2000
		US 2002110638 A1	15-08-2002
		US 2002136934 A1	26-09-2002
		US 2002119307 A1	29-08-2002
		US 2002150681 A1	17-10-2002
		US 2003207028 A1	06-11-2003
		US 6326079 B1	04-12-2001
		US 2002028361 A1	07-03-2002
EP 0901991	A	JP 11079788 A	23-03-1999
	17-03-1999	EP 0901991 A2	17-03-1999
US 2002045073	A1	AU 3922502 A	27-05-2002
	18-04-2002	CA 2417936 A1	23-05-2002
		EP 1315682 A2	04-06-2003
		WO 0240417 A2	23-05-2002
		US 2003235720 A1	25-12-2003
JP 2000131513	A	12-05-2000	NONE